

SECTION 706 CONCRETE WALKS, DRIVES AND INCIDENTAL PAVING

MATERIAL		REFERENCE	PURP.	SAMPLED BY	MIN. FREQ.	MIN. QUANT.	CERT.	SMALL QUANTITY	TYPICAL HANDLING TIME	REMARKS
		TESTED BY		METHOD		CONTAINER	DISTR.			
CONCRETE (Class M)	Mix Designs, Materials & Tests	706.02		SEE SECTION 901 OF THIS MANUAL.						Air entrainment is required for slip forming.
CURING MATERIALS		706.02 1011.01 Mat. Lab	Accept.	SEE SECTION 601 OF THIS MANUAL.						
JOINT FILLER	Preformed Bituminous Type	706.02 706.03(e)(1) 1005.01(c) Mat. Lab	Accept.	Proj. Engr. S 601	1/5000 lin ft	36 in. length	-----	2000 yd ²	10 days	-----
REINFORCING STEEL		706.02 1009.01 Mat. Lab	Accept.	SEE SECTION 601 OF THIS MANUAL.						

I-90

8/02